



**NOTES:**

1. COMPACT EXISTING ROCK MATERIAL TO 98% DENSITY PER A.A.S.H.T.O. T-180.
2. ASPHALT CONCRETE PAVEMENT JOINTS SHALL BE MECHANICALLY SAWED.
3. PERMANENT ASPHALT REPLACEMENT SHOULD BE TWICE EXISTING THICKNESS (2P). (MAXIMUM 2" IN ONE LIFT)

CITY OF PLANTATION  
ENGINEERING STANDARDS  
PLANTATION, FLORIDA

SCALE:  
N.T.S.  
REVISED:  
11-14-13

PARKING LOT  
ASPHALT REPAIR  
DETAIL AND NOTES