



## CROSS SECTION

SCALE: N.T.S.

### NOTES:

1. PORTLAND CEMENT SHALL CONFORM TO ASTM. SPECIFICATION C-150.
2. AGGREGATES SHALL CONFORM TO ASTM. SPECIFICATION C-33.
3. AVERAGE COMPRESSIVE STRENGTH OF PAVER BRICKS SHALL BE NOT LESS THAN 8000 P.S.I. WITH NO INDIVIDUAL BRICK LESS THAN 7200 P.S.I. IN ACCORDANCE WITH TESTING PROCEDURES OF ASTM. STANDARD C-140.
4. AVERAGE ABSORPTION SHALL NOT BE GREATER THAN 5% WITH A MAXIMUM TOLERANCE NOT TO EXCEED 7%.
5. THE SAND LEVELING COURSE SHALL BE A WELL GRADED CLEAN WASHED SHARP SAND WITH 100% PASSING A  $\frac{3}{8}$ " SIEVE SIZE AND A MAXIMUM OF 3% PASSING A No. 200 SIEVE SIZE. MASON SAND NOT BE USED. MAXIMUM THICKNESS OF SAND SHALL BE 1 INCH.
6. ALL EDGES OF PAVER BRICKS SHALL BE RESTRAINED AS SHOWN ON SKETCH.
7. ALL UNSUITABLE, UNSTABLE AND ORGANIC MATERIAL SHALL BE REMOVED PRIOR TO SUBGRADE PREPARATION.
8. THE PAVER BRICKS SHALL BE INSTALLED IN A MANNER AND PATTERN AS REQUIRED BY MANUFACTURER'S SPECIFICATIONS.

CITY OF PLANTATION  
ENGINEERING STANDARDS  
PLANTATION, FLORIDA

SCALE:  
N.T.S.

REVISED:  
11/12/09

RESIDENTIAL PAVER  
DRIVEWAY DETAIL